

## Uniseal 150

### One Part Low Modulus Polyurethane Sealant

#### Description

Uniseal 150 is a high performance one part low modulus polyurethane sealant specifically developed for the sealing of contraction and expansion joints in civil engineering and building structures.

**Standards Compliance:** EN 15651-1

#### Advantages

- One part therefore easy to apply
- Excellent resistance to weathering
- Permanently flexible
- Low odour
- 25 % total joint movement


#### Applications

- Movement joints in concrete, masonry & blockwork
- Perimeter pointing around window & door frames
- Water treatment plants & waste water treatment works
- Parapet walls on highway structures

#### Technical Information

Type	Thixotropic polyurethane
Colours	Black or grey
Application temperature	5 to 40°C
Service temperature range	-20 to 80°C
Cure rate	>2.5 mm per 24 hours
Tack free time	75 minutes
Tensile & Elongation	1.3 MPa & >250 %
Elastic resilience	>70 %
Ability to move	25 %
Shore A hardness	15 - 25
100 % Modulus of Elasticity	0.15 - 0.25 MPa
Chemical resistance	To water, cleaning agents, spillage of oils & hydrocarbons, acids & dilute alkalis
U.V. resistance	Excellent

Note: All testing performed at 23°C & 50 % RH

 0074/0071	
Nufins, Kingston House, 3 Walton Road, Pattinson North, District 15, Washington, Tyne & Wear, NE38 8QA  13  000811005	
EN 15651-1  Type F EXT-INT (25LM)	
Polymer base	Polyurethane
Fire behaviour	Class E
Dangerous substances	Assessed
Resistance to flow	≤3 mm
Loss of volume	≤10 %
Adhesion/Cohesion properties	No failure
Durability	Conforms

#### Preparation of Substrate

All joints should be dry, sound, free from dirt, dust and grease. Cleaning should be carried out by wire brushing or grinding. Joint sides must be parallel and straight.

#### Placing of Backer Rod

Following preparation of the joint, place a backer rod or bond breaker tape to regulate the depth of the sealant and prevent adhesion to the expansion joint filler.



## Priming

Apply one coat of Uniseal Primer P2 and allow to dry for between 45 minutes and 2 hours.

## Application Instructions

Before starting application, ensure that any primer or cleaner has dried fully. Cut the end of the sachet with a sharp knife and place the sachet into a 600 ml Nufins Barrel Gun. Extrude the sealant into the base of the joint and ensure that full contact is made with the sides. Care should be taken to avoid trapping air within the sealant.

## Tooling

Select a tool to suit the width of the joint and wet it with clean water containing a little detergent. Working upwards in the case of vertical joints, lightly tool the sealant into the joint. On completion of the tooling remove masking tape immediately if it has been used.

## Coverage

Shown in metre per 600 ml of sealant (approximations only)

Depth of Joint (mm)	Width of Joint (mm)				
	4	6	8	12	20
6		16	12	8	5
8			9	6	3
10				5	3

Primer P2 coverage approximately 400 m run, at 15 mm depth, per litre.

## Packaging

Uniseal 150 is available in 12 No x 600 ml sachets per box.

Uniseal Primer P2 is available in 1 litre packs.

## Cleaning of Tools

Tools should be cleaned with Nuwash solvent as soon as possible after use.

## Storage

The shelf life is 12 months when stored unopened in dry, normal conditions and away from direct sunlight. Protect from frost.

## Health & Safety

Product Safety Data Sheets (SDS) are available from Nufins. SDS sheets are provided to help customers satisfy their safe handling, use and disposal needs as well as assist with any conformance requirements made locally by health and safety regulations.

SDS are continually updated to provide the latest information to our customers. We therefore recommend contacting our head office to obtain the most recent and accurate SDS before handling and using any product.

## Disclaimer

The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied themselves independently as to the suitability of our products for their own particular purpose. In no event shall Nufins be liable for consequential or incidental damages.

Users must always refer to the most recent issue of the Technical Datasheets, copies of which will be supplied on request.

## Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors. Technical contacts are available to provide further information and arrange demonstrations.